
Fasson® 2.3M White BOPP TC/C2510/50#SCK**Spec# 79141****Facestock:**

Fasson® 2.3 Mil White BOPP TC is a heat set, biaxially-oriented, coextruded polypropylene film, with good opacity and a bright white high gloss background. The surface has been topcoated to provide superior printability by UV and water-based flexographic, gravure, silkscreen and letterpress processes, using a wide variety of different inks. This facestock has excellent moisture resistance, and good diecutting and dispensing characteristics.

Basis Weight:	n/a
Caliper:	0.0023 inches $\pm$ 10%
Tensile:	MD 26,825 psi CD 22,475 psi
Tear:	N/A
Stiffness:	N/A

Adhesive:

Fasson® C2510 is a rubber-based adhesive featuring high initial tack and ultimate bond strength to a wide variety of substrates, including low surface energy plastics, glass, and corrugated cardboard. C2510 was engineered specifically for cold, damp environments typical of dairy environments. C2510 has very good high speed/wide web converting characteristics. This adhesive is suitable for applications which require compliance with FDA 175.105. This section covers applications where incidental contact between food and the adhesive could occur.

Type:	Hot melt rubber
Minimum Application Temperature:	+25° F
Service Temperature Range:	-65° F to +160° F

Typical Performance Data: 50# Dairy Label at room temperature on standard lab panels

HDPE

Loop Tack:	3.2 lbs
Peel Adhesion:	1.8 lbs

LDPE

Loop Tack:	2.7 lbs
Peel Adhesion:	1.6 lbs

Corrugated

Loop Tack:	1.5 lbs
Peel Adhesion:	1.6 lbs

Liner:

50# SCK is a bleached super-calendered kraft stock featuring high internal strength, toughness and tear resistance. Ideally suited for marginal punching, perforating and fanfolding.

Basis Weight:	N/A
Caliper:	0.0032 inches $\pm$ 10%
Tensile:	N/A
Tear:	N/A

Total Construction Caliper (approximate): 0.0063 inches $\pm$ 10%

Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

Statement of Practical Use

All materials, sales and contracts for sale of Avery Dennison products are sold with the express requirement and understanding that the customer is solely and exclusively responsible for testing and for ensuring the products are fit for the customer's purposes or an end-user's purposes. All express or implied warranties of merchantability and fitness for particular use are disclaimed.

Warranty

All sales and contracts for sale are expressly conditioned on the buyer's assent to Avery Dennison's terms and conditions found on its website at www.na.fasson.com. Avery Dennison hereby objects to any term, different from or additional to Avery Dennison's terms, contained in any buyer communication in any form, unless agreed to in a writing signed by an officer of Avery Dennison.

www.na.fasson.com



Label and Packaging Materials -North America

8080 Norton Parkway
Mentor, OH 44060
800-944-8511

